



TECHNICAL SPECIFICATION

Carpet Underlay Own Label 60

Cellular sponge rubber carpet underlay

End Use Classification (BS 5808: 1991): LD/U, Light Domestic Use

Guaranteed for the serviceable lifetime of the carpet when used in the recommended locations

Roll size: 15.07 sqm of 1.37 m x 11.0 m

Specification	BS Requirements	Result	Method
Nominal square weight		1800 g/m ² (56 oz/sq yd)	
Nominal thickness		6.7 mm	BS 4051
Mean original thickness from nominal thickness	Maximum 12%	3.5 %	
Difference between max. & min. original thicknesses	Maximum 3mm	0.3 mm	
Work of compression	Minimum 50 J/m ² after dynamic loading for 1000 impacts	52 J/m ²	BS 4098 & BS 4052
Compression after dynamic loading	Minimum 2mm, maximum 7mm after 1000 impacts	4.0 mm	
Retention of work of compression	Minimum 40% of original after 1000 impacts	51 %	
Breaking strength - length	Minimum 40N	182 N	BS 2576
Breaking strength - width		126 N	
Extension under force - length	Maximum 10% @ 40N	2.2 %	
Extension under force - width		1.0 %	
Loss in thickness after dynamic loading	Maximum 15% after 1000 impacts	12 %	BS 4052
Loss in thickness after static loading	Maximum 15% after 24hrs loading & recovery	13 %	BS 4939
Resistance to cracking	Not greater than 50mm	Pass	BS 5808
Odour		No objectionable odour	
Colour and appearance		Gold sponge rubber waffle with brown Textron paper backing	
Thermal Properties			
Thermal resistance		1.2 tog	BS 4745
Acoustic Properties			
Weighted reduction in impact sound pressure level (Delta Lw)		30 dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997

Please note: This document does not constitute a manufacturing specification. It details important technical performance and physical characteristics of the product only. Please contact the Technical Department for any further information.

Carpets Direct (GB) Ltd Unit 3 Riverside Works Reservoir Road Hull HU6 7QD

Tel: +44(0)1482 215008 Web: www.TradePriced.co.uk